

MONOCARBON PRIME WB

Cold Applied Bitumen Emulsion

Description

MONOCARBON PRIME WB is a thixotropic bitumen emulsion designed for applications as a primer and sealer coat. The coating is dark brown in color and dries to black flexible protective film. The finished films are tough and forms a barrier to water and vapor transmission.

Uses

MONOCARBON PRIME WB is used for general waterproofing, damp-proofing and protective coating for below ground concrete structures against attack by ground salts. This can also be used as the protective coating for built-up roofing systems and other exposed surfaces, as a damp proofing membrane or as vapor seal.

It is used as primer coat prior to the application of torch applied bituminous waterproofing membranes.

Advantages

- Cold applied, Easy to apply
- Quick drying
- Non-flammable
- Can be applied over damp surfaces
- Excellent adhesion to concrete, metal and wood.

Technical Properties

Color:	Dark Brown	-
Specific Gravity @ 25 °C:	1.0 (±0.02)	ASTM D2939
Solid Content:	32% (±2)	ASTM D2939
Firm set @ 25 °C	24 hours	-
Flash Point:	Non-Flammable	
Service Temperature:	5 °C – 75 °C	

All values given are subject to 5-10% tolerance.

MONOCARBON PRIME WB conforms to the requirement of ASTM D 1227 - Type III, class 1. The drying time depends on the type of substrate, temperature, humidity and thickness.

Surface Preparation

Ensure that surface to be treated is sound and free from all oil, grease and other foreign matters. Cracks, potholes and honey combs are to be repaired with a suitable material from the 'CARBON' range of repair mortars.

Priming

Primer is always recommended prior to coating, as it not only seals the porous substrates but also acts as an adhesion promoter for further coatings. The primer coat can be made in the site by diluting **MONOCARBON PRIME WB** with 10-15% of water. The primer may be applied by brush, roller or spray. Allow the primer to dry before any further coats are applied. However, if the primer coat is left open for more than 24 hours after it becomes dry, clean the surface of any settled dust and apply first coat of primer.

Cleaning: Clean tools immediately after use in a strong soap solution. Keep brushes soaking in this solution between applications. Hardened it needs physical scraping followed with treatment in white spirit.

Coverage: Depending on the dry film thickness required, apply the **MONOCARBON PRIME WB** at 4-5 m²/Lit./coat.

Packaging: **MONOCARBON PRIME WB** is supplied in 200 Litre Drum, 20 Litre and 15 Litre Pail.

Storage: The drums & pails must be stored in a covered area, away from direct sunlight and protected from extreme temperature.

SHELF LIFE Keep away from direct sunlight and store under normal warehouse conditions. Container must be tightly closed. Shelf life of this product is 12 months from the date of manufacturing.

Cautions

Health and Safety

It is non-hazardous and non-flammable emulsion. Always wear hand gloves, safety shoes and safety goggles while using and handling this product. Avoid contact with skin and eyes. When contact with eyes, wash with plenty of water and seek medical facilities immediately.

Disclaimer

STARKE products are guaranteed against defective materials and are sold subject to standard terms and condition of sale, copies of which are available on request which are reasonable, care is taken compiling this technical data sheet, all recommendations regarding the use of product are made without guarantee since the conditions of use are beyond the company's direct control. It is the customer's responsibility to satisfy them that each product is fit for the purpose for which they intend to use it.

Furthermore the specifications and description herein cannot be used to void a contract.

More from starke construction chemicals A wide range of construction chemical products are manufactured by STARKE which include:

Concrete admixtures.

Surface treatments

Grouts and anchors.

Concrete repair.

Flooring Coating

Sealants.

Waterproofing.

Adhesives.



Starke Polymer Ltd
Plot 158, kampala uganda

Tel + 256 787 288 087
Tel + 256 708 693 991

Email: info@starkepolymers.com
www.Starkepolymers.com