

MONOBIND EP

Two component , thixotropic, epoxy adhesive
for Concrete and steel, Pvc .

Description

MONOBIND EP is a slow cure, solvent-free epoxy resin bonding agent that is supplied in pre-weighted two component packs which when mixed together produce a medium viscosity epoxy adhesive.

MONOBIND EP can be easily spread over old concrete or cementitious substrates and Metal, pvc to permanently bond freshly casted concrete or new mortars.

Applications

MONOBIND EP is a permanent epoxy adhesive for bonding fresh wet concrete/cementitious material to old concrete/ cementitious surfaces, metal, pvc which is suitable for internal and external application.

Advantages

- High bond strength.
- Moisture tolerant; can be applied to damp surfaces.
- Bonding steel to concrete
- Bonding slabs and pipes in concrete and fibre reinforced concrete.
- High strength.

Standards

MONOBIND EP complies with ASTM C881 Type II, Grade 2, Class C.

Method of Use

SUBSTRATE PREPARATION

MONOBIND EP The Substrate should be sound, clean and free from contamination. Surface laitance should be removed by acid etching or light grit blasting. Oil, grease, and fat deposit should be removed by using either appropriate degreaser or steam cleaning. Weak or deteriorated concrete should be removed by scabbling, chipping or grit blasting.

Mixing

The base and the hardener should be mixed separately before mixing together to disperse any settlement.

Carefully transfer the entire contents of the hardener container into the base component container and thoroughly mix using slow speed drill with appropriate mixing paddle for 3 minutes until uniformity is obtained. Do not attempt to mix partially nor add any thinning materials.

Technical Properties

Colour:	PART A	PART B
	Grey	Yellowish grey
Mixed colour	Dark Grey	
Mixed density:	1.4 ± 0.1 g/cm ³	
Compressive	≥ 50 MPa @7 days	
Cure	Substrate	Temperature
	Moist/Damp	Conditions
14 days	Concrete Moist	-
		≥ 10Mpa
	Full Cure	
7 days	Concrete dry	25 °C
		> 14Mpa
5 days	Concrete dry	40 °C
		> 16Mpa
7 days	Steel	25 °C
		> 20Mpa

Typical minimum	2 hrs @ 25°C
overlay time:	1 hr @ 40°C
Typical maximum	9 hrs @ 25°C
overlay time:	5 hrs @ 40°C
Gel time:	6 hrs @ 25 °C

ASTM C881

Viscosity: 40 ± 10 poise @ 25°C

Minimum and maximum overlaying times depend on the ambient weathering conditions. In general the new concrete/cementitious material should be only applied over tacky layer of Quickmast 108. Quickmast 108 is designed to have an overlaying

time of 9 hours at 25 °C and 5 hours at 40 °C. This should allow for subsequent works such as steel reinforcement fixation and shutter erection.

Permeability:

APPLICATION

MONOBIND EP should be applied immediately after mixing using a short haired paint brush. The material should be painted evenly across the whole surface and left until it becomes tacky (typically 2 hours at 25 °C and 1 hour at 40 °C) before the new concrete, screed or mortar is placed.

Care should be taken to apply the new concrete, screed or mortar within the overlay time specified in Technical Properties.

Failure to do so will have an adverse result and the material will form a de-bonding plane rather than a bonding coat.

Minimum application temperature is 5°C while temperatures exceeding 35°C will decrease pot life and setting time.

NOTES

- If temperature of the material is less than 12°C, it is needed to elevate their temperature to 25°C before the application.
- And if the ambient and the substrate temperature is less than 5°C, don't use the material.
- Also, at high temperatures (35°C and above), cooling the material is needed before the application. And try not to make the application in the middle of the day or under direct sunlight.

Cleaning

All tools should be cleaned immediately after finishing by STARKE solvent. Hardened materials should be cleaned mechanically.

Packaging

MONOBIND EP is available in 1 kg (0.7 litre) and 5 kg packs (3.6 litre).

COVERAGE

2.5 - 3.0 m²/kg.

Storage

MONOBIND EP has a shelf life of 18 months from date of manufacture if stored at temperatures between 15°C and 30°C.

If these conditions are exceeded, STARKE Technical Department should be contacted for advice.

Cautions

Health and Safety

MONOBIND EP should not come in contact with skin or eyes.

Rubber gloves and eye protection should be worn all the time. The use of barrier cream is recommended on exposed areas of the skin.

In case of contact with eye, rinse with clean water and seek medical consultation.

For further information refer to the Material Safety Data Sheet.

Fire

MONOBIND EP is nonflammable.

More from starke construction chemicals A wide range of construction chemical products are manufactured by STARKE which include:

Concrete admixtures.

Surface treatments

Grouts and anchors.

Concrete repair.

Flooring Coating

Sealants.

Waterproofing.

Adhesives.



Starke Polymer Ltd
Plot 158, kampala uganda

Tel + 256 787 288 087
Tel + 256 708 693 991

Email: info@starkepolymers.com
[www. Starke polymers.com](http://www.Starkepolymers.com)