

MONO PP FIBER

Mono Polypropylene Fiber

PRODUCT DESCRIPTION

MONO PP Fiber is a high-performance monofilament polypropylene fiber which is developed to reduce cracking during the curing of concrete and improve the strength of cohesiveness and surface quality of concrete. It is suitable for hot and tropical climate, also is used in mixtures to increase the strength in bending and tension. PP

Fiber is an economical and quality alternative to steel mesh controls the formation of cracks.

Raw Material	Polypropylene	Crack Elongation	20+/-5%
Fiber Type	monofilament	Fiber Diameter	20µm-30µm
Melting Point (C Deg.)	160 - 170	Density(g/cm3)	0.91 +/-0.01
Acid & Alkali Resistance	Strong	Tensile Strength (MPa)	>450 min.
water absorbency	NO	Length:	Times of 4mm or 6mm
Normal length	4mm, 6mm, 8mm, 12mm, 18mm, 24mm, 30mm etc... (times of 4mm or 6mm with 1mm more or less)		

ADVANTAGES:

- . Reduce shrinkage and cracking concrete
- . Replace reinforcing mesh.
- . Increase the strength in bending and tension
- . Does not rust, disperses uniformly throughout the mix
- . Improves concrete freezing-thawing resistance
- . Improve impact resistance of concrete, folding resistance, fatigue resistance, seismic performance

Improve the durability of concrete and aging resistance

APPLICATION SCOPE:

- . Various Types of Concrete, Shotcrete
- . Cementitious overlays, stamped concrete, screeds, driveways, render mortars
- . Industrial & Warehouse floors
- . Patch repair on precast elements
- . Water Retaining Structures

APPLICATION INSTUCTION:

A) . Dosage: For resist the common cracks on surfaces, recommend dosage is 0.9kg / m3.

For increasing reinforcement and seepage resistance, recommend dosage is 1.8kg / m3.

B). Mixing requirement: The proportion of cement, sand and aggregate is no need to be changed. Put cement, aggregate, additive and fiber together, then mix after adding enough water and time for mixing can be prolonged for 2~3 minutes to make the compound mix completely. Also, it can be mixed with cement and other aggregates in advance, rotating by adding water at worksite before construction.

PACKING:

Normal packing is 0.6kg, 0.9kg or 1.0kg per bag.

Also, it can be packed upon request.



Starke Polymers Ltd.,

Administrative Office:

Plot No. 158, Kampala, Uganda

Contacts. +256 787 288 087

+256 708 693 991

Email. info@starkepolymers.com

www.starkepolymers.com

Important note :

Starke range products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Starke endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation, opinion or information given by it.